

# DOCK/ CHEMICALS

SEMICONDUCTORS DECISION



Aluminum precursor for MOCVD & ALD

MO-CVD

BP: 50 °C / 122 °F (0.05 Torr)

DMEAI- DIMETHYLETHYLAMINE ALANE ADDUCT

PRODUCT DATASHEET

# 'DMEAAI- DIMETHYLETHYLAMINE ALANE ADDUCT

## IDENTIFICATION

<b>CAS-No:</b>	124330-23-0
<b>EC-No:</b>	-
<b>Other name:</b>	-

'MO-CVD

## PHYSICAL PROPERTIES

<b>Vapor pressure:</b>	1.5 Torr (25 °C)
<b>Density:</b>	0.837 g/cm <sup>3</sup>
<b>Molweight:</b>	103.14 g/mol
<b>Melting point:</b>	5 °C / 41 °F
<b>Boiling point:</b>	50 °C / 122 °F (0.05 Torr)

## CHEMICAL PROPERTIES

<b>Stability:</b>	Stable under inert gas
<b>State of matter:</b>	Liquid

## SAFETY & TRANSPORT

<b>Toxicity:</b>	Pyrophoric
<b>Explosion limit Vol%:</b>	Pyrophoric
<b>Auto ignition temp. °C:</b>	Pyrophoric
ADR/RID	
<b>ADR/RID-class:</b>	4.2(4.3)
<b>UN-no:</b>	3394, PG I
IMDG	
<b>IMDG -class:</b>	4.2(4.3)
<b>UN-no:</b>	3394, PG I
ICAO/IATA	
<b>ICAO/IATA-class:</b>	4.2(4.3)
<b>UN-no:</b>	3394, PG I – AIRFREIGHT FORBIDDEN

For further details please refer to Safety Data Sheet (SDS)

## PACKAGING & STANDARD FILLING VOLUMES

<b>DMEAAI.100.DOCK/10.150</b>	100g / 150ccm cyl.
<b>DMEAAI.250.DOCK/10.400</b>	250g / 400ccm cyl.
<b>DMEAAI.400.DOCK/10.600</b>	400g / 600ccm cyl.
<b>DMEAAI.750.DOCK/10.1000</b>	750g / 1000ccm cyl
<b>DMEAAI.2000.DOCK/10.3000</b>	2000g / 3000ccm cyl.

## QUALITY STANDARDS

**EG Electronic Grade**

## VAPOR PRESSURE CURVE

n.a.

## APPLICATION

III/V MOCVD, ALD

**'DOCK/  
CHEMICALS**

SEMICONDUCTORS DECISION

**Dockweiler Chemicals GmbH**

Emil-von-Behring-Strasse 76 35041 Marburg Germany

T +49 6421 396 -380 | F +49 6421 396 -381

sales@dockchemicals.com

**PRODUCT DATASHEET**

www.dockchemicals.com